

Product Information:

KK-SICO487 is a thermoplastic, halogen free flame retardant natural jacketing compound with high mechanical strength, durability, UV resistance and excellent extrusion properties.

Typical features of the KK-SICO487 product,

- Excellent processing properties
- No need for pre-drying
- High mechanical strength and toughness
- Low water permeability
- No need for pre-drying
- UV resistance

The properties of this compound comply with the requirements of,

EN 50363-8 TM7

BS 7655 LTS3

VDE 0207 Teil 24 (HM2)

EN 50290-2-27

EN 50288

Product Data:

Property	Test Method	Unit	Value
Physical Properties			
Melt Flow Rate (190°C-2,16 kg)	ASTM D 1238	g/10 min	0,9
Density (23°C)	ASTM D-792	g/cm ³	1,15
Hardness	ISO 868	Shore D	45
Mechanical Properties			
Tensile Strength	ISO 527	MPa	16
Elongation at Break	ISO 527	%	650
Heat Ageing (100 °C, 240 h)	IEC 60811		
Δ Strength		%	≤ 20
UV Ageing	IEC 60811		
Δ Strength		%	≤ 20
Tear Strength	ASTM D 1938	N/mm	15
Hot Pressure (Test at 80 °C, 4 h)	IEC 60811-508	%	<50
Cold Flex	ISO 458-2	°C	-40±2
Cold Bend (-40°C ±2 °C)	IEC 60811-504	-	No Cracks
Cold Impact (-40°C ±2 °C)	IEC 60811-506	-	Pass
Chemical Properties			
Halogen Content	EN 60754-1	%	<0,5 Max.
pH	IEC 60754-2	-	>4.3
Conductivity	IEC 60754-2	μS/mm	<10
Water Absorption (70°C, 168 h)	IEC 60811-402	mg/cm ²	<1
LOI	ISO 4589	%	29
Smoke Density	EN-61034	% transmittance	>80
Other Properties			
DC Volume Resistivity	IEC 60093	PΩcm	6
Oil IRM 902 oil (70 °C, 4 h)	IEC 60811-404		
Δ Strength		%	10
Δ Elongation		%	9

Processing:

Extrusion Temperatures: 120°C–130°C–140°C–150°C–160°C

Packaging: It is packaged as 1000 kg in octabin.

Storage&Handling:

KK-SICO487 should be stored in a manner that avoids direct exposure to sunlight and heat (T<30°C). This compound should be used within 6 months after its production date. After this time it's necessary to dry the material before extrusion.

KABKOM KİMYA SANAYİ VE TİCARET A.Ş.

İbni Melek OSB TOSBİ Yol 1 No:13 PK:35900 Tire/İZMİR

Tel: +90 (216) 807 20 04 (pbx)

www.kabkom.com.tr

info@kabkom.com.tr

satis@kabkom.com.tr

