

**SC-FRB1****Aluminum Composite Panel Compound****Product Applications:**

SC-FRB1 is aluminum composite panel B1 compound based on polyolefin resin.

**Recommendation of addition rate:**

FRB1+%20 PE	:B1 Panel
FRB1+%10 PE	: High FR Panel

**Product Data**

Property	Test Method	Unit	Value
<b>Physical Properties</b>			
Carrier Resin	-	-	PE
Color	ASTM E 1164	-	Light Grey
MDH Content	-	%	80
MFI (150°C-21,6 kg)	ASTM D 1238	g/10 min	4±2
Density	ASTM D 792	g/cm <sup>3</sup>	1,86±0,03
LOI	ISO 4589	%	>62

**Packaging:**

It is packaged as 1250 kg in bigbag.

**Storage&Handling:**

SC-FRB1 should be stored in a manner that avoids direct exposure to sunlight and heat (T<30°C). This compound should be used within 6 months after its production date. After this time it's necessary to dry the material before extrusion.

**KABKOM KİMYA SANAYİ VE TİCARET A.Ş.**

İbni Melek OSB TOSBİ Yol 1 No:13 PK:35900 Tire/İZMİR

Tel: +90 (216) 807 20 04 (pbx)

[www.kabkom.com.tr](http://www.kabkom.com.tr)

[info@kabkom.com.tr](mailto:info@kabkom.com.tr)

[satis@kabkom.com.tr](mailto:satis@kabkom.com.tr)

