

Product Information:

SX-4E(HM4) is UV thermoplastic halogen free, flame retardant and low smoke emission compound, for cable insulation and sheathing. It can be used for the production of energy, signal and control cables.

Range material operating temperatures : +90°C.

The properties of this compound comply with the requirements of,

TS HD 604 S1 type M1; EN 50363-7 type TI7
IEC 60502 ST8; VDE 0207 Part 24 type HM2-HM4
BS 7655 type LTS1 – LTS2 & LTS3 – LTS4

EN 50290-2-27
UNE 21123-4:2010 – ANNEX A-Table1 type DMZ-E
IEC 60092-360 type SHF1

Product Data:

Property	Test Method	Unit	Value
Physical Properties			
Melt Flow Rate (150°C-21,6 kg)	ASTM D 1238	g/10 min	9
Density (23°C)	ASTM D-792	g/cm ³	1,51
Hardness	ISO 868	Shore D	55
Mechanical Properties			
Tensile Strength	ISO 527	MPa	13
Elongation at Break	ISO 527	%	190
Heat Ageing (110 °C, 168 h)	IEC 60811		
Δ Strength		%	-30
Δ Elongation		%	±40
Tear Strength	ASTM D 1938	N/mm	5
Hot Pressure Test at 90 °C	IEC 60811	%	<50
Cold Flex	ISO 458-2	°C	-40±2
Cold Bend (-15 °C±2 °C)	IEC 60811-504	-	No Cracks
Cold Elongation (-15 °C±2 °C)	IEC 60811-505	-	30 Min.
Cold Impact (-15 °C±2 °C)	IEC 60811-506	-	Pass
Chemical Properties			
Halogen Content	EN 60754-1	%	<0,5 Max.
pH	IEC 60754-2	-	>4.3
Conductivity	IEC 60754-2	μS/mm	<10
Water Absorption	IEC 60811	mg/cm ²	<5.0
LOI	ISO 4589	%	41
Smoke Density	EN-61034	% transmittance	>80
Volume Resistivity 20 °C (Alternating Polarity Method)	ASTM D257 Electrodes	Ω.cm	1.10 ¹⁵
Other Properties			
Oil IRM 902 oil (70 °C, 4 h)	IEC 60811-404		
Δ Strength		%	10
Δ Elongation		%	9

Processing:

Extrusion Temperatures: 115 °C–125 °C–130 °C –135°C–145°C–155 °C (Processing with Die Plate 40 Mesh Filter)

Extrusion Temperatures: 120 °C–125 °C–135 °C –145°C –155°C–165 °C (Processing without Die Plate and Filter)

Packaging:

It is packaged as 1250 kg in octabin.

Storage&Handling: SX-4E(HM4) should be stored in a manner that avoids direct exposure to sunlight and heat (T<30°C). This compound should be used within 6 months after its production date. After this time it's necessary to dry the material before extrusion.

KABKOM KİMYA SANAYİ VE TİCARET A.Ş.

İbni Melek OSB TOSBİ Yol 1 No:13 PK:35900 Tire/İZMİR

Tel: +90 (216) 807 20 04 (pbx)

www.kabkom.com.tr

info@kabkom.com.tr

satis@kabkom.com.tr

