

Product Information:

SX-KYR is a UV resistant or good stress crack resistant thermoplastic, flame retardant and halogen free compound with on polyolefinic basis. It can be used for production of energy, signal and control cables.

Range material operating temperatures : +90°C.

The properties of this compound comply with the requirements of,

TS HD 604 S1 type M1; IEC 60502 ST8

BS 7655 type LTS1-LTS2-LTS3-LTS4

VDE 0207 Part 24 type HM2-HM4

EN 50290-2-27

BS 6724

UNE 21123-4:2010 - ANNEX A-Table1 type DMZ-E

Product Data:

Property	Test Method	Unit	Value
Physical Properties			
Melt Flow Rate (150°C-21,6 kg)	ASTM D 1238	g/10 min	3
Density (23°C)	ASTM D-792	g/cm ³	1,45
Hardness	ISO 868	Shore D	53
Mechanical Properties			
Tensile Strength	ISO 527	MPa	18
Elongation at Break	ISO 527	%	230
Heat Ageing (100 °C, 168 h)	IEC 60811		
Δ Strength		%	< 20
Δ Elongation		%	< 30
Tear Strength	ASTM D 1938	N/mm	9
Hot Pressure Test at 90 °C	IEC 60811	%	<50
Cold Bend (-35 °C±2 °C)	IEC 60811-504	-	No Cracks
Cold Elongation (-35 °C±2 °C)	IEC 60811-505	-	30 Min.
Cold Impact (-35 °C±2 °C)	IEC 60811-506	-	Pass
Chemical Properties			
Environmental Stress Crack Resistance (50°C)	IEC 60811-406	h	>1.000
Halogen Content	EN 60754-1	%	<0,5 Max.
pH	IEC 60754-2	-	>4.3
Conductivity	IEC 60754-2	μS/mm	<10
Water Absorption	IEC 60811	mg/cm ²	<5.0
Water Immersion	BS 6469-9.1		
Δ Strength		%	-30
Δ Elongation		%	-30
LOI	ISO 4589	%	37
Smoke Density	EN-61034	% transmittance	>80
Volume Resistivity 20 °C (Alternating Polarity Method)	ASTM D257 Electrodes	Ω.cm	1.10 ¹⁵
Other Properties			
Oil IRM 902 oil (70 °C, 4 h)	IEC 60811-404		
Δ Strength		%	10
Δ Elongation		%	9
Hydrocarbon Resistance Test	NF M 87-202		
Δ Strength		%	< 40
Δ Elongation		%	< 40

Processing:

Extrusion Temperatures: 115 °C–125 °C–130 °C –135°C –145°C–155 °C (Processing with Die Plate 40 Mesh Filter)

Extrusion Temperatures: 120 °C–125 °C–135 °C –145°C –155°C–165 °C (Processing without Die Plate and Filter)

Packaging:It is packaged as 1250 kg in octabin.

Storage&Handling:SX-KYR should be stored in a manner that avoids direct exposure to sunlight and heat (T<30°C). This compound should be used within 6 months after its production date. After this time it's necessary to dry the material before extrusion.