

**Product Information:**

SX-FLEX8 is UV thermoplastic, flame retardant and halogen free compound on polyolefinic basis. It can be used for production of energy, signal and control cables.

Range material operating temperatures : +80°C.

Properties of this compound comply with the requirements of,

TS HD 604 S1 type M1; EN 50363-7 type TI6  
EN 50363-8 type TM7; EN 50290-2-27  
VDE 0207 Part 24 type HM2-HM4

VDE 0250 Part 215 type HM5  
BS 7655 type LTS1 & LTS3; IEC 60092-360 type SHF1  
IEC 60502 ST8

**Product Data:**

Property	Test Method	Unit	Value
<b>Physical Properties</b>			
Melt Flow Rate (150°C-21,6 kg)	ASTM D 1238	g/10 min	2,5
Density (23°C)	ASTM D-792	g/cm <sup>3</sup>	1,47
Hardness	ISO 868	Shore D	55
ESCR (F0, 50 °C, 10% Igepal) (hours)	IEC 60811-406	No Cracks	>500
<b>Mechanical Properties</b>			
Tensile Strength	ISO 527	MPa	16
Elongation at Break	ISO 527	%	195
Heat Ageing (100 °C, 168 h)	IEC 60811		
Δ Strength		%	-30
Δ Elongation		%	±40
Tear Strength	ASTM D 1938	N/mm	8
Hot Pressure Test at 80 °C	IEC 60811	%	<50
Cold Flex	ISO 458-2	°C	-40±2
Cold Bend (-15 °C±2 °C)	IEC 60811-504	-	No Cracks
Cold Elongation (-15 °C±2 °C)	IEC 60811-505	-	30 Min.
Cold Impact (-15 °C±2 °C)	IEC 60811-506	-	Pass
<b>Chemical Properties</b>			
Halogen Content	EN 60754-1	%	Zero
pH	IEC 60754-2	-	>4.3
Conductivity	IEC 60754-2	μS/mm	<10
Water Absorption	IEC 60811	mg/cm <sup>2</sup>	<5.0
LOI	ISO 4589	%	42
Smoke Density	EN-61034	% transmittance	>80
Volume Resistivity 20 °C (Alternating Polarity Method)	ASTM D257 Electrodes	Ω.cm	1.10 <sup>15</sup>
<b>Other Properties</b>			
Oil IRM 902 oil (70 °C, 4 h)	IEC 60811-404		
Δ Strength		%	10
Δ Elongation		%	9

**Processing:**

Extrusion Temperatures: 115 °C–125 °C–130 °C –135°C–145°C–155 °C (Processing with Die Plate 40 Mesh Filter)

Extrusion Temperatures: 120 °C–125 °C–135 °C –145°C–155°C–165 °C (Processing without Die Plate and Filter)

**Packaging:** It is packaged as 1250 kg in octabin.

**Storage&Handling:** SX-FLEX8 should be stored in a manner that avoids direct exposure to sunlight and heat (T<30°C). This compound should be used within 6 months after its production date. After this time it's necessary to dry the material before extrusion.

**KABKOM KİMYA SANAYİ VE TİCARET A.Ş.**

İbni Melek OSB TOSBİ Yol 1 No:13 PK:35900 Tire/İZMİR

Tel: +90 (216) 807 20 04 (pbx)

[www.kabkom.com.tr](http://www.kabkom.com.tr)

[info@kabkom.com.tr](mailto:info@kabkom.com.tr)

[satis@kabkom.com.tr](mailto:satis@kabkom.com.tr)

