

**Product Information:**

KK-SV8 is an additive masterbatch that increases the crack resistance of HFFR cables and compounds. It also contains UV and heat stabilizers.

**Typical Applications:**

KK-SV8 can be used at a dosage of minimum 7% and maximum 15%.

**Product Data:**

Property	Test Method	Unit	Value
<b>Physical Properties</b>			
Melt Flow Rate (150°C-21,6 kg)	ASTM D 1238	g/10 min	80±10
Density (23°C)	ASTM D 792	gr/cm <sup>3</sup>	1,38±0,03
Moisture Content	Internal Method (110°C)	%	≤0,1
DSC Melting Point	Internal Method	°C	118

**Packaging:**

It is packaged as 25 kg PE bags on 1250 kg pallets.

**Storage&Handling:**

KK-SV8 should be stored in a manner that avoids direct exposure to sunlight and heat. The storage area should also be dry. KABKOM does not provide a warranty for quality deterioration that is a result of faulty storage conditions.

KABKOM KİMYA SANAYİ VE TİCARET A.Ş.

İbni Melek OSB TOSBİ Yol 1 No:13 PK:35900 Tire/İZMİR

Tel: +90 (216) 807 20 04 (pbx)

[www.kabkom.com.tr](http://www.kabkom.com.tr)

[info@kabkom.com.tr](mailto:info@kabkom.com.tr)

[satis@kabkom.com.tr](mailto:satis@kabkom.com.tr)

