

**Product Information:**

SC-CLR0540 is suitable for technical applications, injected molding, casting extrusion and thermoforming, offering good hiding power and dispersion.

**Typical Applications:**

The use of SC-CLR0540 is widely used in many industries, especially in automotive, electronics, packaging, construction, film, injection, sheet, cable and household appliances.

They are products with high carbon content, glossy effect, smooth surface, high covering and dispersion properties, compatible with EVA, PE, PP, HDPE polymers.

Usage recommendation: %1-5

**Product Data:**

Property	Test Method	Unit	Value
<b>Physical Properties</b>			
Carbon Black Content	ASTM D 1603	%	40±1
Specific Weight (23°C)	ASTM D-792	gr/cm <sup>3</sup>	1,15
Melting Point	ASTM 3417	°C	125
Processing Temperature	-	°C	300
Light Fastness	DIN 53388	-	8

**Packaging:**

It is packaged as 25 kg in PE bags, 1000 kg pallets.

**Storage&Handling:**

The SC-CLR0540 should be stored out of direct sunlight and heat (T<30°C). This compound should be used within 2 years from the date of manufacture. After this time, it is necessary to dry the material before extrusion.

**KABKOM KİMYA SANAYİ VE TİCARET A.Ş.**

İbni Melek OSB TOSBİ Yol 1 No:13 PK:35900 Tire/İZMİR

Tel: +90 (216) 807 20 04 (pbx)

[www.kabkom.com.tr](http://www.kabkom.com.tr)

[info@kabkom.com.tr](mailto:info@kabkom.com.tr)

[satis@kabkom.com.tr](mailto:satis@kabkom.com.tr)